

Beam-material issues for instrumentation in a 5 MW monolith

M.A. Hartl, Y. Lee, C. Thomas, J. Habainy, T. Shea (ESS, Sweden)
David Wragg, Erik Adli, Håvard Gjersdal (University of Oslo, Finnland)
W. Blokland (Spallation Neutron Source, USA)
M. Jura (ISIS, Rutherford labs, England)
M. Tomut & group (GSI, Germany)

The ESS facility layout


H⁺ Accelerator:

- 2 GeV/ 2.5 mA avg. (5 MW)
- Long pulse: 2.86 ms/14 Hz

Spallation Target:

- Rotating tungsten target
- Helium cooled

Target




Neutron science systems

Instruments:


- 16 instruments + more

The ESS Target Station Layout




Isometric View



Target Monolith – Beam Diagnostics




Proton Beam Instrumentation Plug



Multi-wire Beam Profile Monitor (Grid) “Harp”

- Used for beam profile monitoring
- 5 layers of horiz./vert./diag. wires
- ESS Material:
 - W (SNS) or SiC (JSNS, ISIS, LANSCE)
- Thickness: 100 μm
- Method: secondary electron emission:
 - SEY: low energy (<1 keV)- Sternglass theory
 - DEY: enough energy to escape and produce further ionization (10 keV-1 MeV, “ δ -rays”) → calculated by particle transport (FLUKA)



Secondary Electron yield at 2 GeV H⁺ Sternglass formula (SEY) / FLUKA (DEY)

- P: probability of e⁻emittance =
0.5 (Bethe-Bohr equipart.)
- d_s: average depth for e⁻ emittance =
1*10⁻⁹ m
- E': average kin. energy lost =
25 eV (solid)
- dE/dz: proton stopping power of wire

Sternglass:

$$SEY = \frac{P * d_s}{E'} \frac{dE}{dz}$$


E_k < 1keV

FLUKA: DEY


larger E

Wire Material	dE/dz [MeV/cm]	SEY E _k <1keV	DEY E _k >10keV	Total Yield
Tungsten	24.4	0.049	0.026	0.075
SiC	5.16	0.010	0.013	0.023



- Benchmark with SNS/LANSCE reasonable



Charge Deposition and Electron Flux at the Harp (FLUKA)



39 wires (2mm pitch)




Radiation Damage & Life time of Harp wires

- Maximum displacement per atom (dpa) at 5 MW H^+ :

Wire Material	Max. dpa Rate [dpa/h]	Annual Operation Time	Max.dpa Rate per Year
Tungsten	0.012	5400	64.8
SiC	0.001	5400	5.4

- SiC wire: JSNS (3GeV, SiC, 0.25 dpa), ISIS (0.8 GeV, SiC, 3 dpa)
 - JSNS/ISIS dpa lower than expected @ ESS (5.2 dpa/year)
 - LANSCE reported failure of one/two wires within 1 year
- W-wire: SNS (1GeV, W harp 70 dpa)
 - ESS current >> SNS current
 - => max. rad damage 70 dpa safe
 - (see beam current density/accumulated beam)




No use of W alloys for harp wires @ ESS

- W-wire:
 - **D**uctile-to-**B**rittle-**T**ransition-**T**emperature (DBTT) increases with rad. damage
 - higher operation T: W can self-anneal? W/Re not
 - W alloys: reduced life time (BLIP/CERN)

- DBTT (W) $\ll$ DBTT (W-10% Re)
for DPA > 0.3


[H. Ullmaier, F. Carsughi, NIMB 101 (1995)]

alloys W/Re are excluded for ESS




Aperture Monitor

- Material: Nickel, thickness 100 μm (PSI (0.575 GeV) has operated more than 2 decades without failure)
- Electron yields:



Facility	dE/dz [MeV/cm]	SEY $E_k < 1\text{keV}$	DEY $E_k > 10\text{keV}$	Total Yield
PSI	16.7	0.033	0.023	0.056
ESS	13.6	0.027	0.019	0.046



6 Ni sheets covering
horizontal range
(20 cm)



Net Charge Deposition is negative: incoming, fast e^- are stopped in Ni blades (instead of only H^+),
need to change position of monitor

Beam imaging system: Luminescence Coating On Target and PBW


Optical pathway (only one shown)



Coated steel samples






**Coated Aluminum
surface samples (Jülich,
Stony Brook).**




Luminescence coating: Cr-doped Alumina at SNS

- SNS target coating material => Cr^{3+} doped Al_2O_3 sprayed on target,
 - Achieved 2D map of beam!
 - Material degrades in the radiation field within days to <10% luminescence.
 - Oxygen lines appear, ruby lines decrease




Decrease in luminescent efficiency with irradiation



Luminescence coating for ESS: Cr-doped Alumina?

- Start point: SNS target coating material
 - Material degrades in the radiation field over time
 - Contamination from particles emanating from the target (similar to SNS)
 - No more pre-cursor powder available !? (maybe new supplier)

luminescence measurement



ESS

- higher neutron flux than SNS
- ESS target change only every 5 years or so (SNS every 8 months)
- **Quenching of luminescence at higher temperature (~200 deg. C) due to He cooling of W**

Planned & performed characterization of luminescence material

- **What is special about the pre-cursor material for the luminescent screen?**
 - chemical & structural characterization (XRD, ND, N-PDF, NVS, XAFS)
VOODOO?
- **Degradation due to radiation ?**
 - irradiation of coated PBW samples at BNL's BLIP facility
 - looking for partners for post-irradiation examination (LANL, ORNL, ..)
 - Ongoing Work with SNS on in-situ luminescence screen
 - heavy ion irradiation (GSI: June 2016), further measurements

Voodoo – or not?


- X-ray Fluorescence (no standard)

Pre-cursor Voodoo powder		Sprayed powder
Al ₂ O ₃	95.2%	<i>Currently being measured</i>
Cr ₂ O ₃	3.8 %	
P ₂ O ₅	0.6	
Ag ₂ O	0.2 %	


- Nuclear Magnetic Resonance (NMR):
 - No organic substances found.
- XRD (will be compared to neutron diffraction &PDF)

Pre-cursor Voodoo powder		Sprayed powder
Al ₂ O ₃	99.5% (corundum)	Cr-substituted Corundum (ruby) (Al _{1.926} Cr _{0.074} O ₃) 39.8%
Cr ₂ O ₃	0.5%	ε- Al-oxide (Al ₂ O ₃) 60.1%

Luminescence measurements under heavy-ion bombardment (^{238}U)



Displacement per atom in 1%Cr-Al₂O₃



The damage rate in the coating at 5MW beam power is **$8 \cdot 10^{-5}$ dpa/h**

GSI beamtime:

Accumulated total fluence of
 $1 \cdot 10^{12}$ U/cm².

This translates to total dpa of:

$1.8 \cdot 10^{-3}$ dpa at 20 μm

1d at 5 MW

$1.8 \cdot 10^{-5}$ dpa at 1 μm

15 min at 5 MW

Testing of potential candidates for luminescence screen

- Optimizing the established material
 - Cr-content
 - spray conditions
 - (choice of starting material)
- Understanding why the material works
 - VOODOO pre-cursor works - other “identical” materials do not
 - further characterization of Voodoo material and resulting sprayed material
- Understanding why the material degrades in the radiation field and what the mechanism is:
 - Oxygen lines due to reduction of Cr^{3+} when the proton beam hits?
 - Local areas of elemental Cr and O_2 ?
 - Characterization/ comparison before/after irradiation.
- Development of “new”, radiation-resistant materials:
 - yttria, zirconia, YAG,...

Thank you...

